UK
West Fraser Europe Ltd
Station Road
Cowie
Stirling
Scotland
FK7 7BQ
DoP ref: NP6Strebord_UKCA_DoPv3
EN13986:2004 +A1:2015
1224
21
E1
P6
38mm T&G
Structural use in dry conditions

Essential characteristics	Performance
	Thickness(mm)
	38mm T&G at 600mm Centres
¹Characteristic Strength (N/mm²)	
- Bending f_m	11.7
- Compression f_c	11.9
- Tension f_t	7.8
- Panel Shear $f_{ m u}$	6.0
- Planar shear f_r	1.7
¹Mean Stiffness (MOE) (N/mm²)	
- Tension E _t	1800
- Compression E _c	1800
- Bending E _m	3100
- Panel Shear <i>G_v</i>	900
Punching Shear Characteristic strength under point load F _{max, k} (kN) (for floors and roofs)	12.93
Punching Shear Mean stiffness under point load, R _{mean} (N/mm) (for floors and roofs)	1980
Racking resistance (for walls) Characteristic Strength F _{Rd,max,k} (N)	NPD
Racking resistance (for walls) Mean Stiffness R _{mean} (N/mm)	NPD
Soft Body Impact resistance	
Floor/roofs Walls.	Impact Class 1, Pass, Floor
Embedment Strength f _h (N/mm2)	NPD

	Minimum thickness	Class (excluding floorings)g	Class (Flooring) ^h	
Without an air gap behind the panel ^{abef}	9	D-s2,d0	C _{fl} ,s1	
With a closed or open air gap ≤ 22mm behind the panel cef	9	D-s2,d2	-	
Closed air gap behind the panel def	15	D-s2,d0	C _{fl} ,s1	
With an open air gap behind the panel ^{def}	18	D-s2,d0	C _{fl} ,s1	
Any end use ef	3	Е	Efl	

²Reaction to fire

(see notes to table for field of application details and associated documentation references)

- a -Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10kg/m3 or at least class D-s2, d2 products with minimum density 400 kg/m3.
- b -A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings.
- c -Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m3.
- d -Mounted with an air gap behind. The reverse face of the cavity shall be at least class D-s2, d2 products with minimum density 400 kg/m3.
- e -Veneered, phenol- and melamine-faced panels are included for class excl. floorings.
- f -A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m² can be mounted in between the wood-based panel and a substrate if there are no air gaps in between.
- g -Class Provided for in Table 1 of the Annex to decision 2000/147/EC
- h -Class Provided for in Table 2 of the Annex to decision 2000/147/EC

Essential characteristics		Performance						
Water vapour permeability μ		NPD						
Release of formaldehyde		E1						
Release (content) of pentachlorophenol (PCP)		≤5ppm						
Airborne sound insulation (surface mass) R (dB)		NPD						
³ Sound absorption Frequency range 250Hz to 500Hz (α)		0.1						
³ Sound absorption Frequency range 1000Hz to 2000Hz (α)		0.25						
Thermal conductivity λ (W/m.K)		NPD						
Air Permeability V ₀ (m3/h)		NPD						
	Durability							
Internal bond (N/mm²)		0.30						
Swelling in thickness (%)		14						
⁴ Mechanical (creep k _{def}) Service class 1		1.5						
Mechanical (duration of load k _{mod})		Action Mode						
	Permanent	Long Term	Medium Term	Short Term	Instantaneous			
Service Class 1	0.30	0.45	0.65	0.85	1.1			
Biological		Use classes 1 & 2						

NOTES TO TABLE

- 1 Taken from EN 12369-1:2001
- 2 reaction to fire classes from Table 1 of Commission Decision 2003/43/EC of January 2003 (OJEU L13 of 18.1.2003) corrected by Corrigendum (OJEU L33 of 8.2.2003) and amended by Commission decision 2007/348/EC of May 2007 (OJEU L131 of 23-05-2007); also reproduced in Table three of EN 13986:2004+A1:2015 for wood-based panels installed according to CEN/TR 12872
- 3 Taken from Table 10 of EN 13986:2004+A1:2015
- 4 Taken from Eurocode 5 EN 1995-1-1 2004+A2:2014