

DECLARATION OF PERFORMANCE

DoP Reference number: - NL.MDF.H_UKCA_DoPv3

Wet Fraser Europe Ltd

Station Road

Cowie

Stirling

FK7 7BQ

Unique identification code of the product type	Intended use	Systems of AVCP	Approved Body	Designated standard
L-MDF.H >9mm to 45mm*	Internal use as non-structural components in humid conditions	4	Not Applicable	EN13986:2004 +A1:2015
*The unique identification of the product-type is a combination of the technical class and the individual product's nominal thickness				

Declared performance (covering a range of product-types L-MDF.H >9mm to 45mm*)

Essential characteristics	Performance			
	Thickness (mm)			
	>9 to 12	>12 to 19	>19 to 30	>30 to 45
¹ Water vapour permeability μ	NPD	NPD	NPD	NPD
Release of formaldehyde	E1	E1	E1	E1
Release (content) of pentachlorophenol (PCP)	≤ 5 ppm	≤ 5 ppm	≤ 5 ppm	≤ 5 ppm
² Airborne sound insulation (surface mass) R (dB)	NPD	NPD	NPD	NPD
³ Sound absorption Frequency range 250Hz to 500Hz (α)	0.1	0.1	0.1	0.1
³ Sound absorption Frequency range 1000Hz to 2000Hz (α)	0.2	0.2	0.2	0.2
⁴ Thermal conductivity λ (W/m.k)	NPD	NPD	NPD	NPD
Air Permeability V_0 (m ³ /h)	NPD	NPD	NPD	NPD
Durability				
Internal bond (N/mm ²)	0.45	0.45	0.45	0.40
Swelling in thickness (%)	16	13	12	11
Internal bond after cyclic test (N/mm ²)	0.25	0.20	0.15	0.10
Swelling in thickness after cyclic test (%)	16	15	15	15
Biological	Use classes 1 & 2			

⁵ Reaction to fire (see notes to table for field of application details and associated documentation references)		Minimum thickness	Class (excluding floorings) ^g	Class (Flooring) ^h
	Without an air gap behind the panel <small>abef</small>	9	D-s2,d0	D _{fl} ,s1
	With a closed or open air gap ≤ 22mm behind the panel <small>cef</small>	9	D-s2,d2	-
	Closed air gap behind the panel <small>def</small>	15	D-s2,d0	D _{fl} ,s1
	With an open air gap behind the panel <small>def</small>	18	D-s2,d0	D _{fl} ,s1
	Any end use <small>ef</small>	3	E	E _{fl}
a Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10kg/m ³ or at least class D-s2, d2 products with minimum density 400 kg/m ³ . b A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings. c Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m ³ . d Mounted with an air gap behind. The reverse face of the cavity shall be at least class D-s2, d2 products with minimum density 400 kg/m ³ . e Veneered, phenol- and melamine-faced panels are included for class excl. floorings. f A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m ² can be mounted in between the wood-based panel and a substrate if there are no air gaps in between. g Class Provided for in Table 1 of the Annex to decision 2000/147/EC h Class Provided for in Table 2 of the Annex to decision 2000/147/EC				
NOTES TO TABLE				
1 Taken from Table 9 of EN 13986:2004+A1 2 Calculated according to clause 5.10 of EN 13986:2004+A1 3 Taken from Table 10 of EN 13986:2004+A1 4 Taken from Table 11 of EN 13986:2004+A1 5 reaction to fire classes from Table 1 of Commission Decision 2003/43/EC of January 2003 (OJEU L13 of 18.1.2003) corrected by Corrigendum (OJEU L33 of 8.2.2003) and amended by Commission decision 2007/348/EC of May 2007 (OJEU L131 of 23-05-2007); also reproduced in Table 8 of EN 13986:2004+A1:2015 for wood-based panels installed according to CEN/TR 12872				

The performance of the product identified is in conformity with the declared performance.

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 as it has effect in the United Kingdom in respect of Great Britain, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of West Fraser Europe Limited:

Stuart Hendry (General Manager)



At: Cowie, Scotland Date: 1st October 2024