

## DECLARATION OF PERFORMANCE

DoP Reference Number: - NP5Strebord\_UKCA\_DoPv2

**West Fraser Europe Ltd**

**Station Road**

**Cowie**

**Stirling**

**FK7 7BQ**

Unique Identification code of the product type*	Intended Use	Systems of AVCP	Approved Body	Designated standard
P5 38mm*	Internal use as structural components in humid conditions	2+	1224	EN13986:2004 +A1:2015
<small>*The unique identification code of the product type is a combination of the technical class and the individual product's nominal thickness</small>				

### Declared performance (covering P5 38mm\*)

Essential characteristics	Performance
	Thickness(mm)
	38mm T&G at 600mm Centres
<sup>1</sup> Characteristic Strength (N/mm <sup>2</sup> )	
- Bending $f_m$	8.3
- Compression $f_c$	8.5
- Tension $f_t$	5.6
- Panel Shear $f_v$	4.8
- Planar shear $f_r$	1.2
<sup>1</sup> Mean Stiffness (MOE) (N/mm <sup>2</sup> )	
- Tension $E_t$	1400
- Compression $E_c$	1400
- Bending $E_m$	2400
- Panel Shear $G_v$	690
<b>Punching Shear Characteristic strength under point load <math>F_{max, k}</math> (kN)</b> <i>(for floors and roofs)</i>	12.54
<b>Punching Shear Mean stiffness under point load, <math>R_{mean}</math> (N/mm)</b> <i>(for floors and roofs)</i>	1960
<b>Racking resistance (for walls)</b> <b>Characteristic Strength <math>F_{Rd, max, k}</math> (N)</b>	NPD
<b>Racking resistance (for walls)</b> <b>Mean Stiffness <math>R_{mean}</math> (N/mm)</b>	NPD
<b>Soft Body Impact resistance</b> <b>Floor/roofs</b> <b>Walls.</b>	Impact Class 1, Pass, Floor
<b>Embedment Strength <math>f_h</math> (N/mm<sup>2</sup>)</b>	NPD

<sup>2</sup> Reaction to fire  (see notes to table for field of application details and associated documentation references)		Minimum thickness	Class (excluding floorings) <sup>g</sup>	Class (Flooring) <sup>h</sup>
	<b>Without an air gap behind the panel</b> <sup>abef</sup>	9	D-s2,d0	D <sub>fi</sub> ,s1
	<b>With a closed or open air gap ≤ 22mm behind the panel</b> <sup>cef</sup>	9	D-s2,d2	-
	<b>Closed air gap behind the panel</b> <sup>def</sup>	15	D-s2,d0	D <sub>fi</sub> ,s1
	<b>With an open air gap behind the panel</b> <sup>def</sup>	18	D-s2,d0	D <sub>fi</sub> ,s1
	<b>Any end use</b> <sup>ef</sup>	3	E	E <sub>fi</sub>
a -Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10kg/m <sup>3</sup> or at least class D-s2, d2 products with minimum density 400 kg/m <sup>3</sup> . b -A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings. c -Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m <sup>3</sup> . d -Mounted with an air gap behind. The reverse face of the cavity shall be at least class D-s2, d2 products with minimum density 400 kg/m <sup>3</sup> . e -Veneered, phenol- and melamine-faced panels are included for class excl. floorings. f -A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m <sup>2</sup> can be mounted in between the wood-based panel and a substrate if there are no air gaps in between. g -Class Provided for in Table 1 of the Annex to decision 2000/147/EC h -Class Provided for in Table 2 of the Annex to decision 2000/147/EC				

Water vapour permeability $\mu$	NPD				
Release of formaldehyde	E1				
Release (content) of pentachlorophenol (PCP)	≤5ppm				
Airborne sound insulation (surface mass) R (dB)	NPD				
<sup>3</sup> Sound absorption Frequency range 250Hz to 500Hz ( $\alpha$ )	0.1				
<sup>3</sup> Sound absorption Frequency range 1000Hz to 2000Hz ( $\alpha$ )	0.25				
Thermal conductivity $\lambda$ (W/m.K)	NPD				
Air Permeability $V_0$ (m <sup>3</sup> /h)	NPD				
<b>Durability</b>					
Internal bond (N/mm <sup>2</sup> )	0.30				
Swelling in thickness (%)	9				
Internal bond after cyclic test (N/mm <sup>2</sup> )	0.15				
Swelling in thickness after cyclic test (%)	9				
<sup>4</sup> Mechanical (creep $k_{def}$ ) Service class 1	2.25				
<sup>4</sup> Mechanical (creep $k_{def}$ ) Service class 2	3				
Mechanical (duration of load $k_{mod}$ )	<b>Action Mode</b>				
	Permanent	Long Term	Medium Term	Short Term	Instantaneous
Service Class 1	0.30	0.45	0.65	0.85	1.1
Service Class 2	0.20	0.30	0.45	0.60	0.80
Biological	Use classes 1 & 2				

NOTES TO TABLE

1 Taken from EN 12369-1:2001

2 reaction to fire classes from Table 1 of Commission Decision 2003/43/EC of January 2003 (OJEU L13 of 18.1.2003) corrected by Corrigendum (OJEU L33 of 8.2.2003) and amended by Commission decision 2007/348/EC of May 2007 (OJEU L131 of 23-05-2007); also reproduced in Table three of EN 13986:2004+A1:2015 for wood-based panels installed according to CEN/TR 12872

3 Taken from Table 10 of EN 13986:2004+A1:2015

4 Taken from Eurocode 5 EN 1995-1-1 2004+A2:2014

The performance of the product identified is in conformity with the declared performance.

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 as it has effect in the United Kingdom in respect of Great Britain, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

John Robb

At: - Cowie, Scotland

On: - 03-07-2023

Two handwritten signatures in blue ink, one on the left and one on the right, both appearing to be variations of the name 'John Robb'.