

West Fraser Europe Limited
Hill Village
South Molton
Devon
EX36 4HP

DoP ref: WFSMP4LPDoPv5			
EN13986:2004 +A1:2015			
0502			
04			
E1			
P4			
10mm to 38mm			
Structural use in dry conditions			

Essential characteristics	Performance			
	Thickness(mm)			
	18mm 1200x0300mm T&G 2 edges			
¹Characteristic Strength (N/mm²)				
- Bending $f_m$	12.5			
- Compression $f_c$	11.1			
- Tension $f_t$	7.9			
- Panel Shear $f_{ u}$	6.1			
- Planar shear $f_r$	1.6			
¹Mean Stiffness (MOE) (N/mm²)	1700			
- Tension E <sub>t</sub>	1700			
- Compression E <sub>c</sub>	1700			
- Bending E <sub>m</sub>	2900			
- Panel Shear G <sub>v</sub>	830			
Punching Shear Characteristic strength under point load				
F <sub>max, k</sub> (kN)	NPD			
(for floors and roofs)				
Punching Shear Mean stiffness under point load, R <sub>mean</sub>				
(N/mm)	NPD			
(for floors and roofs)				
Racking resistance (for walls)	NPD			
Characteristic Strength F <sub>Rd,max,k</sub> (N)	INFD			
Racking resistance (for walls)	NPD			
Mean Stiffness R <sub>mean</sub> (N/mm)	וערט			

Soft Body Impact resistance Floor/roofs Walls.		NPD					
Embedment Strength f <sub>h</sub> (N/mm2)		NPD					
	Minimum thickness	Class (excluding floorings) <sup>g</sup>	Class (Flooring) <sup>h</sup>				
Without an air gap behi panel <sup>abef</sup>	nd the 9	D-s2,d0	D <sub>fl</sub> ,s1				
With a closed or open air 22mm behind the pan	J .	D-s2,d2	-				
Closed air gap behind the panel	e panel 15	D-s2,d0	D <sub>fl</sub> ,s1				
With an open air gap beh panel <sup>def</sup>	ind the	D-s2,d0	D <sub>fl</sub> ,s1				
<sup>2</sup> Reaction to fire Any end use <sup>ef</sup>	3	E	E <sub>fl</sub>				
(see notes to table for field of application details and associated documentation references)  a -Mounted without an air density 10kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3.  d -Mounted without an air density 10kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3.  d -Mounted without an air density 10kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind. The reverse face of density 10 kg/m3 or at leas substrate of cellulose insul directly against the wood-lehind.	a -Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10kg/m3 or at least class D-s2, d2 products with minimum density 400 kg/m3. b -A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings. c -Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m3.						

f -A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m $^2$  can be mounted in between the wood-based panel and a substrate if there are no air gaps in between. g -Class Provided for in Table 1 of the Annex to decision 2000/147/EC h -Class

faced panels are included for class excl. floorings.

Provided for in Table 2 of the Annex to decision 2000/147/EC

Essential characteristics	Performance			
	Thickness(mm)			
	18mm 1200x0300mm T&G 2 edges			
Water vapour permeability μ	NPD			
Release of formaldehyde	E1			
Release (content) of pentachlorophenol (PCP)	≤5ppm			
Airborne sound insulation (surface mass) R (dB)	NPD			
<sup>3</sup> <b>Sound absorption</b> Frequency range 250Hz to 500Hz (α)	0.1			
<sup>3</sup> Sound absorption Frequency range 1000Hz to 2000Hz (α)	0.25			
Thermal conductivity λ (W/m.K)	NPD			
Air Permeability V <sub>0</sub> (m3/h)	NPD			
Durability				
Internal bond (N/mm²)	0.35			

Swelling in thickness (%)		15			
<sup>4</sup> Mechanical (creep k <sub>def</sub> ) Service class 1		2.25			
<b>Mechanical</b> (duration of load k <sub>mod</sub> )		Action Mode			
	Permanent	Long Term	Medium Term	Short Term	Instantaneous
Service Class 1	0.30	0.45	0.65	0.85	1.1
Biological			Use classes 1	•	

## NOTES TO TABLE

- 1 Taken from EN 12369-1:2001
- 2 reaction to fire classes from Table 1 of Commission Decision 2003/43/EC of January 2003 (OJEU L13 of 18.1.2003) corrected by Corrigendum (OJEU L33 of 8.2.2003) and amended by Commission decision 2007/348/EC of May 2007 (OJEU L131 of 23-05-2007); also reproduced in Table three of EN 13986:2004+A1:2015 for wood-based panels installed according to CEN/TR 12872
- 3 Taken from Table 10 of EN 13986:2004+A1:2015
- 4 Taken from Eurocode 5 EN 1995-1-1 2004+A2:2014